



## Technical Data Sheet

# BILO Floor Wax No. 303

<b>Range of application</b>	For wood, cork and open-pored stone floors after pre-treatment with LIVOS oils. Not suitable for moist areas.
<b>Technical qualities</b>	Silky gloss, elastic, anti-static finish.
<b>Full declaration</b>	Linseed oil, beeswax, carnauba wax, orange oil, Isoaliphates and Dammar resin.
<b>Color</b>	Clear.
<b>Application method</b>	Apply with brush, cotton cloth, spatula or polishing machine.
<b>Coverage</b>	1 liter (1.06 fl. quart.) is sufficient for 75-95 m <sup>2</sup> (807 – 1022 ft <sup>2</sup> ) per coat, i.e. 12 ml/m <sup>2</sup> . Coverage could be considerably less depending on the condition and absorbency of the surface. Always do a test application!
<b>Drying Time</b>	At 23°C (73°F) and 50 % relative humidity, 24 - 48 hours. Do not walk on floors until completely dry.
<b>Specific gravity</b>	Approximately 0.85 g/ml.
<b>Safety advice</b>	<p>Always be sure to store and dispose cleaning cloths, polishing pads, sponges, etc. that are still wet or even slightly moist with BILO Floor Wax No. 303 in an airtight metal container or in water, as there is a danger of spontaneous combustion caused by the linseed oil in the product.</p> <p>The product alone will not undergo spontaneous combustion. Contains Limonene S 2     Keep out of the reach of children S 62    If swallowed, do not induce vomiting; seek medical advice immediately and show this container or label</p>
<b>Disposal</b>	According to locally regulated laws.
<b>Container Sizes</b>	0.2 lt; 0.375 lt; 2.5 lt.
<b>Storage</b>	Cool and dry please see label for expiry date. Please, smooth the surface after use, close lid tightly and use within 3 months.  See reverse for Application Instructions.

## How to use

# BILO Floor Wax No. 303

- Preparation**                    The surface must be saturated with a LIVOS oil product.
- Application**                    Pre-treatment has to be completely dry. After a minimum of 24 - 48 hours, apply a very thin coat of BILO Floor Wax with a cloth, wax brush or spatula (for hot wax application, use No. 307).  
Warning: Applying too thickly can cause surface to be sticky and difficult to polish. Any puddles of wax will develop a whitish film upon drying; using a short-haired, medium-hard brush, for example, helps to avoid such problems.  
Polishing of treated wood floors must be done with strong force in the direction of the grain after 24h at the earliest, with a wadded cloth, a polishing brush, a heavy duty manual polisher, or electric floor polisher. An even, silky gloss finish should develop that, after the dissipation of frictional heat, should not be sticky to the touch. On the next day, after further drying, polish again. Repeated polishing in subsequent weeks will make the floor more and more wear-resistant.
- Important tips**                    During the first 3 weeks after application treat newly waxed surfaces with great care. For short, limited usage, cover surface with corrugated cardboard or another diffuse-able material.  
Rugs or carpets are not yet to be laid permanently on treated surfaces, and under no circumstances should the surface be washed with water during the drying time. Sand, moisture and dirt do the biggest damage to the floor before drying is complete.  
Simplifying of the wax application is possible through warming in a water bath, but PLEASE NOTE that the product will become inflammable through this process.
- Care**                                 Remove dust with vacuum cleaner or mop.  
Rubber scuffs and other heavy soiling can be removed with SVALOS Thinner No. 222.  
Depending upon the degree of use of the surface, re-treat the surface 1 - 2 times a year with GLEIVO Beeswax No. 315 or BIVOS Oil Wax No. 375. Clean surface with TRENA pH-Neutral Cleaner No. 556 as needed.
- Renovation**                    Thoroughly clean heavily worn, soiled, or otherwise damaged areas with LATIS Natural Intensive Cleaner No. 551 or TRENA pH-Neutral Cleaner No. 556, sand and re-oil if necessary, then re-wax with a thin coat of BILO Floor Wax No. 303 or SOGO Universal Hard Wax No. 307 and polish.

**These directions are the result of long years of research and practical testing. They are backed by our most current expert information. New findings may invalidate this information. This data sheet is meant to serve as information and instruction. No legal liability should be interpreted from it. In case of doubt, please contact the retailer, wholesaler, or manufacturer.**